

## RESIMETAL 108 水激活增强带 – 水激活，快速固化管道堵漏增强带

产品为高性能，快速固化水激活堵漏&增强带，开袋浸泡吸水后用于管道的堵漏及增强修复。

- 用于经手工处理或机械打磨后的管道表面
- 快速固化 – 完全固化30分钟
- 耐压性能达到72.5psi 至 218psi

**应在进行堵漏缠绕前，对管道进行泄压处理。**

### 固化时间

在20°C下，进行以下作业前按下述时间放置固化，温度越高时间越短，反之亦然：

|      |       |
|------|-------|
| 操作时间 | 3 分钟  |
| 完全固化 | 30 分钟 |

### 包装规格

产品有以下包装规格 –

50mm x 1.8mtr  
50mm x 3.6mtr  
75mm x 3.6mtr  
100mm x 3.6mtr

### 颜色

固化后 - 白色

### 再次涂覆时间

最短 - 触摸干燥后可以再次缠绕

最长 - 20°C下不应超出1小时

如超出最长再次涂覆时限，再次施料前应对表面进行打磨/快速的喷砂处理。

### 储藏时限

干燥、常温未开封下(15-30°C) 1年

### Other Technical Documents

|                             |   |                                   |
|-----------------------------|---|-----------------------------------|
| Quick Application Guide     | - | Hand application                  |
| Safety Data Sheets          | - | Single component                  |
| Product Specification Sheet | - | Technical Performance Information |

### Health and Safety

Please ensure good practice is observed at all times. Protective gloves, goggles & a disposable coverall must be worn during the mixing and application of this product. Before mixing and applying the material ensure you have read the fully detailed Safety Data Sheet.

#### Legal Notice:

The data contained within this Technical Data Sheet is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine if the product is suitable for use. Resimac accepts no liability arising out of the use of this information or the product described herein.

Resimac Ltd, Unit B, Park Barn Estate, Station Road, Topcliffe, Thirsk, YO7 3SE, United Kingdom

Tel: +44 1845 577498 Email: [info@resimac.co.uk](mailto:info@resimac.co.uk) Web: [www.resimacsolutions.com](http://www.resimacsolutions.com)

TDS108.rv3.08052019