

RESICHEM 523 墙面涂层

Resichem 523墙面涂层，产品为单组份，水基丙烯酸涂层。设计用于外部表面的防水，抗紫外线及耐风化防护。单组份产品使用简便，适用于混凝土，石膏，砌砖及石棉水泥表面。

主要应用

混凝土，砌砖，石膏板，石棉水泥等外部表面。

特征

外观
单组份：

触变型
丙烯酸乳浆

混合比
单组份产品

密度
1.25

固含量
60%

抗流挂性能
350 微米下为 0

覆盖率
刷涂或辊涂施工：具体膜厚根据项目而定，参考膜厚：300微米湿膜厚度

3.33m²每升

固化时间

涂覆后的产品，应按下述时间放置固化：

触干		
10°C	2-4	小时
20°C	1-2	小时
30°C	30-60	分钟
40°C	15-30	分钟

最短再次涂覆时长

10°C	6-8	小时
20°C	3-4	小时
30°C	1.5-2	小时
40°C	45-60	分钟

最长再次涂覆时长

无限制

储存时限

常温(15-30°C)，干燥，未开封
下为 2年

机械性能

延展性
按 ASTM D412标准
120%

拉伸剪切
按ASTM D412标准
56kg/cm² (800psi)

拉脱粘接力
按 ASTM D4541标准
28kg/cm² (400psi)

渗水率
按 ASTM D1653标准
2 x 10⁴ perm.cm

耐热性能
可耐高达 120°C 干热。

耐潮性能

按BS3900标准
5000 小时无影响

抗霉菌性能
极佳

抗细菌性能
极佳

Quality

All Resimac Products are supplied under the scope of the company's fully documented quality system.

Warranty

Resimac warrants that the performance of the product supplied will conform to the typical descriptions quoted within this specification provided material is stored correctly and used according to the procedures detailed in the Technical Data Sheet for the material.

Health and safety

Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves and other recommended personal protective equipment must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read and fully understood the detailed Material Safety Data Sheet

Legal Notice: The data contained within this Product Specification is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Resimac accepts no liability arising out of the use of this information or the product described herein.