

## RESICHEM 551 紧急防水涂层

产品为单组分，溶剂型丙烯酸防水涂层。用于屋顶及沟渠的紧急防水施工。

### 主要应用

产品操作简单，适用于屋顶，沟渠，罐底及玻璃钢结构的紧急防水。

### 特征 外观

单组分:

触变型  
丙烯酸  
乳浆

**混合比**  
单组分

**密度**  
1.35

**固含量**  
70%

**抗流挂性能**  
1000 微米下为 0

**覆盖率**  
**刷涂或刮涂施工:**  
具体膜厚根据项目确定。

1mm 湿膜厚度 1m<sup>2</sup> 每升  
2mm 湿膜厚度 0.5m<sup>2</sup> 每升

### 固化时间

涂覆后的产品应按下述时间放置固化，时间随温度成正比:

### 抗暴雨

10°C 30 分钟  
20°C 15 分钟  
30°C 7.5 分钟

### 触干

10°C 24 小时  
20°C 12 小时  
30°C 6 小时

### 最长再次涂覆

无限制

### 储存时限

常温(15-30°C), 干燥, 未开封  
下为 5年

### 机械性能

#### 延展性

按ASTM D412标准  
100%

#### 拉升剪切

按ASTM D412标准  
42kg/cm<sup>2</sup> (600psi)

#### 拉脱测试

按 ASTM D4541标准  
16kg/cm<sup>2</sup> (230psi)

#### 抗渗透性能

按ASTM D1653标准  
2 x 10<sup>4</sup> perm.cm

#### 耐温性能

最高可耐100°C干热。

### Quality

All Resimac Products are supplied under the scope of the company's fully documented quality system.

### Warranty

Resimac warrants that the performance of the product supplied will conform to the typical descriptions quoted within this specification provided material is stored correctly and used according to the procedures detailed in the Technical Data Sheet for the material.

### Health and safety

Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves and other recommended personal protective equipment must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read and fully understood the detailed Material Safety Data Sheet

**Legal Notice:** The data contained within this Product Specification is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Resimac accepts no liability arising out of the use of this information or the product described herein.