

RESICHEM 556

防水微孔涂层

产品为单组分，水基透明

防水涂层。

用于多孔砌体结构的防水屏障层。

主要应用

产品为浓缩包装，混合时加水稀释。用于水泥，混凝土，石块及砖块表面。

特征外观

单组分:

近透明液体

混合比

单组分

密度

1.35

固体含量

按9:1的清水及556浓缩料混合后，为10%。

抗流挂性能

75 微米时为 0

覆盖率

刷涂, 辊涂或喷涂施工:

涂膜厚度根据基材材质确定。
平整混凝土表面 2.6m²(28ft²) 每升

粗糙混凝土 1.3m² (14 ft²) 每升

平整砌砖2.6m² (28 ft²) 每升

砖块 1.3m² (14 ft²) 每升

水泥质2.6m² (28 ft²) 每升

天然石块 2.1m² (22.75 ft²) 每升

固化时间

涂覆后的产品应按以下时间放置

固化。时间随温度成正比:

触干

10°C 4 小时

20°C 2 小时

30°C 1 小时

40°C 30 分钟

最短再次涂覆时长

10°C 8 小时

20°C 4 小时

30°C 2 小时

40°C 60 分钟

最大再次涂覆时长

10°C 96 小时

20°C 48 小时

30°C 24 小时

40°C 12 小时

储存时限

常温(15-30°C), 干燥, 未开封
下为 2年

Quality

All Resimac Products are supplied under the scope of the company's fully documented quality system.

Warranty

Resimac warrants that the performance of the product supplied will conform to the typical descriptions quoted within this specification provided material is stored correctly and used according to the procedures detailed in the Technical Data Sheet for the material.

Health and safety

Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves and other recommended personal protective equipment must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read and fully understood the detailed Material Safety Data Sheet

Legal Notice: The data contained within this Product Specification is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Resimac accepts no liability arising out of the use of this information or the product described herein.